



SK52524

High Speed Durable Near Edge Resin

Technical Data Sheet



Product Description

SK52524 delivers print speeds of up to 26 IPS (660 mm per second), making it an excellent choice for high-speed flexible packaging applications. In addition to its outstanding performance, it surpasses competitors in abrasion resistance and is well suited for demanding industries such as parts packaging, medical devices, cosmetics, healthcare, and pharmaceuticals. SK52524 is engineered with advanced anti-static and backcoat properties to protect printheads and extend their lifespan. Like all SK ribbons, it leads in edge definition, producing dark, dense images for improved scan accuracy.

Applications



Food & Beverage



Health & Beauty



Pharmaceutical

Recommended Substrates

Synthetics

- ✓ Polyester
- ✓ Polypropylene
- ✓ Polyethylene
- ✓ Polyolefin

Specialty Materials

- ✓ Nylon

Performance Characteristics

- ✓ Halogen-Free
- ✓ Extremely fast print speeds up to 26 IPS (660mm per second)
- ✓ Perfect for prime retail flexible packages
- ✓ Remarkable image density
- ✓ Superior abrasion resistance
- ✓ Unbeatable edge definition for dark, dense images and improved scan rates
- ✓ Anti-static for easy handling and extended printhead life
- ✓ DNP's specially formulated backcoating for printhead protection

More Info



RIBBON PROPERTIES

Description	Result	Test Method
Ink	Resin	
Color	Black	Visual
Total Thickness	5.7 ± 0.9μ	Weight
Base Film Thickness	4.0 ± 0.4μ	Weight

DURABILITY OF PRINTED IMAGE

Description	Result	Test Method
Print Density	> 1.40	Densitometer
Smudge Resistance	A*	Colorfastness Tester - 100 Cycles @ 500 Grams with Cotton Cloth
Scratch Resistance	A*	Colorfastness Tester - 50 Cycles @ 200 Grams with Stainless Steel Pointed Tip

Label Stock: Polypropylene Film

Print Speed: 2 to 26 IPS

*American National Standard Institute (ANSI) Grade Levels A, B, C, D, and F, where A is excellent, B is above average, C is average, D is below average, and F is poor.



The information on this data sheet was obtained in DNP laboratories. Measured values may vary slightly when tested in a different environment. Information contained within this document is subject to change without notification.

PT. Mitra Nippon Printing Indonesia

Kawasan Industri Multiguna 2, Jalan Tanjung No. 3-5, Cikarang Selatan 17530, Indonesia.